

## TenCate Cetex® TC1000 Premium

### PRODUCT TYPE

Polyetherimide (PEI) thermoplastic resin system

### SERVICE TEMPERATURE

149°C (300°F) continuous

### TYPICAL APPLICATIONS

- Aircraft interiors
- Secondary aircraft structures

### CUSTOMER QUALIFICATIONS

- BMS 8-353 (Type 1)
- ABS 5036
- AIMS 003-01
- ASNA 5054

### PRODUCT DESCRIPTION

TenCate Cetex® TC1000 Premium is an engineered thermoplastic composite, utilizing polyetherimide resin for outstanding toughness and excellent fire performance. TenCate Cetex® Premium has gained qualification at Airbus, Boeing and many other airframe OEMs and Tier 1 suppliers for use in aircraft interior and secondary structures.

TenCate Cetex® is typically supplied in 3.66m x 1.22m (12ft x 4ft) pre-consolidated laminates (RTL) of varying ply thicknesses, specifically adhering to customer designated fiber selection, orientation and ply count.

The use of Cetex® as an reinforced thermoplastic laminate (RTL) composite significantly reduces the production cycle-time by eliminating the handling and assembly of traditional wet-lay materials, along with the potential for error. In addition, the thermoplastic forming time is calculated in minutes and seconds, not hours. Heating, forming and cooling can take less than 5 minutes for complex 3D geometry, and sandwich panels can now be realized in 15 minutes without the inconvenience of core read-through. Further optimization can be gained in secondary processing, due to the thermoplastic resin. These operations can include welding, folding, painting and printing.

### TENCATE CETEX® TC1000 PREMIUM PRODUCT BENEFITS / FEATURES

- Excellent FST performance (OSU <15/15)
- No freezer storage required
- Rapid processing with cycle times <3 min
- Very low moisture absorption
- Good solvent resistance
- Low CTE and CME
- Qualified and certified to OEM specifications
- Optional colour grades available

# PRODUCT DATASHEET



TENCATE ADVANCED COMPOSITES

## TenCate Cetex® TC1000 Premium

### NEAT RESIN PROPERTIES - TENCATE CETEX® TC1000 PREMIUM

Property	Test Methods	
Specific gravity	ISO 1183	1.27 g/cm <sup>3</sup>
Glass transition temperature	-	217°C (423°F)
Dielectric constant	ISO D150	3.15 at 1 MHz
Loss tangent	-	0.0013 at 1 MHz
Moisture absorption	ISO 62	1.25%
Flammability	UL94	V-0
Tensile strength	ISO R527	105 MPa (15.2 ksi)
Tensile modulus	ISO R527	3,276 MPa (0.475 Msi)
Elongation at yield	ISO R527	7%
Poisson's ratio	-	0.36
Compression strength	ASTM D695	152 MPa (22.0 ksi)
Compression modulus	ASTM D695	3,310 MPa (0.48 Msi)
Izod notched	ASTM D256	53.4 J/m (1.0 ft-lb/in)
CTE	-	5.58/°C <sup>-1</sup> (3.1/°F <sup>-1</sup> )
Thermal conductivity	-	0.22 W/m·°K

### PHYSICAL / THERMAL PROPERTIES OF PREPREG - TENCATE CETEX® TC1000 PREMIUM - 7781 / PEI

Property	Value
Mass of fabric	296g/m <sup>2</sup> (8.85oz/yd <sup>2</sup> )
Mass of fabric + resin	450g/m <sup>2</sup> (13.27oz/yd <sup>2</sup> )
Resin content by volume	50%
Resin content by weight	33%
Moisture pick up	0.35%
Ply thickness	0.24mm (0.0094in)
Specific gravity	1.91g/cm <sup>3</sup> (119.1lb/ft <sup>3</sup> )
T <sub>g</sub> (DSC) (amorphous)	217°C (423°F)
T <sub>m</sub>	310°C (590°F)

7781 = Glass fabric 296gsm FAW, 8 Harness Satin weave  
PEI = Polyetherimide resin

# PRODUCT DATASHEET



TENCATE ADVANCED COMPOSITES

## TenCate Cetex® TC1000 Premium

### MECHANICAL DATA - TENCATE CETEX® TC1000 PREMIUM

Property	Condition	Methods	Results	
Tensile Strength 0°	RTD	ISA 527 (type 3) EN 2747 (III)	451 MPa	65.4 ksi
Tensile Modulus 0°	RTD	ISA 527 (type 3) EN 2747 (III)	26.3 GPa	3.8 Msi
Compression Strength 0°	RTD	ASTM D 6641 EN 2850	560 MPa	81.2 ksi
Compression Modulus 0°	RTD	ASTM D 6641 EN 2850	29 GPa	4.2 Msi
Flexural Strength 0°	RTD	ISO 178	650 MPa	94.3 ksi
Flexural Modulus 0°	RTD	ISO 178	26 GPa	3.8 Msi

7781 = Glass fabric 296gsm FAW, 8 Harness Satin weave  
PEI = Polyetherimide resin

### FLAMMABILITY PROPERTIES - TENCATE CETEX® TC1000 PREMIUM

Test	Spec	Criteria	2 Plies of 7781 PEI Resin	5 Plies of 7781 PEI Resin	5 Plies of 7781 White PEI Resin
Flammability	60 second vertical burn FAR 25.853 (a)	152 mm	PASS	PASS	PASS
Smoke Emission	ABD0031 (F)	150/200	PASS	PASS	PASS
Toxicity	ABD0031 (F)	Ds Max 4 min (Flaming/Non-Flaming) = 150	PASS	PASS	PASS
Heat Release	FAR 25.853 (d)	2 min Total HR (kWmin/m²) = 65	10.0	0	3.5
		Peak HR (kW/m²) = 65	12.0	13.0	14.1

7781 = Glass fabric 296gsm FAW, 8 Harness Satin weave  
PEI = Polyetherimide resin

Revised 02/2016

All data given is based on representative samples of the materials in question. Since the method and circumstances under which these materials are processed and tested are key to their performance, and TenCate Advanced Composites has no assurance of how its customers will use the material, the corporation cannot guarantee these properties.

TenCate, [TenCate] Cetex® and all other related characters, logos and trade names are claims and/or registered trademarks of Koninklijke Ten Cate N.V. and/or its subsidiaries in one or more country. Use of trademarks, trade names and other IP rights of TenCate without express written approval of TenCate is strictly prohibited.

Page 3 of 3 CETEX\_TC1000\_Premium\_V2\_020416

## TENCATE ADVANCED COMPOSITES

G. van der Muelenweg 2  
7443 RE Nijverdal NL  
Tel: +31 548 633 933  
Fax: +31 548 633 299

Amber Drive, Langley Mill  
Nottingham, NG16 4BE UK  
Tel: +44 (0) 1773 530899  
Fax: +44 (0) 1773 768687

18410 Butterfield Blvd.  
Morgan Hill, CA 95037 USA  
Tel: +1 408 776 0700  
Fax: +1 408 776 0107

[www.tencate.com/thermoplastic](http://www.tencate.com/thermoplastic)

[www.tencate.com/advancedcomposites](http://www.tencate.com/advancedcomposites)  
E-mail: [advancedcomposites.europe@tencate.com](mailto:advancedcomposites.europe@tencate.com) (Europe)  
E-mail: [info@tcac-usa.com](mailto:info@tcac-usa.com) (USA)

ISO 9001  
AS 9100  
Accredited